

## Synergic programs list for Art. 379 – Rev.05 (10/09/2024)

Total number of synergic programs: 97

Material	Alloy	Ø	Gas	Pulse	Pulse HD	Short	Short HD
Fe	SG2 (G3Si1)	0.8mm	Ar+18%CO2	●	●	●	●
		0.9mm		●		●	
		1.0mm		●	●	●	●
		1.2mm		●	●	●	●
		0.9mm	Ar+25%CO2	●		●	●
		1.2mm				●	●
		0.8mm	Ar+8%CO2	●	●	●	●
		1.0mm		●	●	●	●
		1.2mm		●	●	●	●
		1.6mm		●		●	
		0.8mm	100% CO2			●	
		0.9mm				●	
		1.0mm				●	
		1.2mm				●	
Al	AlMg5 (5356)	0.8mm	100% Ar	●		●	
		1.0mm		●	●	●	●
		1.2mm		●	●	●	●
	AlSi5 (4043)	0.8mm	100% Ar	●		●	
		1.0mm		●		●	
		1.2mm		●		●	
SS	308L	0.8mm	Ar+2%CO2	●		●	
		1.0mm		●	●	●	●
		1.2mm		●	●	●	●
		0.8mm	Ar+2%O2	●		●	
		1.0mm		●	●	●	●
		1.2mm		●		●	
	309L	0.9mm	Ar+2%CO2	●		●	
	316L	0.8mm	Ar+2%CO2	●		●	
		1.0mm		●	●	●	●
		1.2mm		●	●	●	●
		0.8mm	Ar+2%O2	●		●	
		1.0mm		●		●	
		1.2mm		●		●	
Special	Basico (E71T-5)	1.2mm	Ar+18%CO2			●	●
	Metal (E70C-6M)	1.2mm	Ar+18%CO2	●		●	
	Rutile (E71T-1)	1.2mm	Ar+18%CO2			●	●
		1.2mm	100% CO2			●	
	Rutile (E81T1)	1.2mm	Ar+18%CO2			●	